

EPALLOY[®] 5000

Hydrogenated Bisphenol A Diglycidyl Ether
CAS No. 30583-72-3

Test Description	Minimum	Maximum	CVC Test Method
Appearance, Clean and Clear	--	Pass	1
EEW, g/eq	210	230	5
Epichlorohydrin Content, ppm	0	10	20
HCC, %	0	0.2	9
Viscosity @ 25 °C, cps	1,300	2,500	4
Water Content, %	0	0.1	8
Solvent Content, %	0	0.1	32

Standard Packaging

Drum: 480 lb..

Pail: 45 lb..

CVC Thermoset Specialties
844 North Lenola Road / Moorestown, NJ 08057
Phone: 856-533-3000 / Fax: 856-533-3003 / www.cvcthermoset.com



An Emerald Performance Materials[®] Company