

# OMICURE® DDA 50

Semi-Micronized Dicyandiamide  
CAS No. 461-58-5

Test Description	Minimum	Maximum	CVC Test Method
Melamine Content, %	0	1.5	46
Moisture, %	0	.5	29
Assay, Nitrogen as Dicyandiamide, %	99	101	C of A
Onset Melting Point by DSC, °C	207	212	22
Particle Size @ 44 microns, %	75	100	64

**Standard Packaging**

**Box: 90 lb.**

CVC Thermoset Specialties  
844 North Lenola Road / Moorestown, NJ 08057  
Phone: 856-533-3000 / Fax: 856-533-3003 / www.cvcthermoset.com



An Emerald Performance Materials® Company