

# OMICURE® DDA 5

Ultra-Micronized Dicyandiamide  
CAS No. 461-58-5

| Test Description                    | Minimum | Maximum | CVC Test Method |
|-------------------------------------|---------|---------|-----------------|
| Melamine Content, %                 | 0       | 1.5     | 46              |
| Moisture, %                         | 0       | .5      | 29              |
| Assay, Nitrogen as Dicyandiamide, % | 99      | 101     | C of A          |
| Onset Melting Point by DSC, °C      | 207     | 212     | 22              |
| Particle Size < 10 microns, %       | 90      | 100     | 64              |
| Particle Size < 7 microns, %        | 50      | 100     | 64              |
| Water Content, %                    | 0       | .5      | —               |
| Particle Size, 100 mesh by AS, %    | 100     | 100     | 65              |

**Standard Packaging**

**Box: 40 lb.**

CVC Thermoset Specialties  
844 North Lenola Road / Moorestown, NJ 08057  
Phone: 856-533-3000 / Fax: 856-533-3003 / [www.cvcthermoset.com](http://www.cvcthermoset.com)



An Emerald Performance Materials® Company