

HyPox[®] RA95

Very High Acrylonitrile Containing Solid Elastomer
Modified Bisphenol A Epoxy Resin
CAS No. 25068-38-6

Test Description	Minimum	Maximum	CVC Test Method
Viscosity @ 52 °C, cps	15,000	30,000	4
Viscosity @ 25 °C, cps	150,000	550,000	4
EEW, g/eq	195	210	5
Water Content, %	0	.1	8
Acid Number	0	.2	7
Gardner Color	0	4	2
Nonvolatiles, %	98	100	13
Volatiles, %	0	2	Calculated

Standard Packaging

Drum: 450 lb.

Pail: 45 lb.

CVC Thermoset Specialties
844 North Lenola Road / Moorestown, NJ 08057
Phone: 856-533-3000 / Fax: 856-533-3003 / www.cvcthermoset.com



An Emerald Performance Materials[®] Company