

# HyPox<sup>®</sup> RFI34I

Epoxy Phenol Novolac Resin Modified with a CTBN Elastomer  
CAS No. 28064-14-4

Test Description	Minimum	Maximum	CVC Test Method
Viscosity @ 25 °C, cps	150,000	300,000	4
EEW, g/eq	285	330	5
Acid Value	-	.2	7

**Standard Packaging**

**Drum:** 450 lb.

**Pail:** 45 lb.

CVC Thermoset Specialties  
844 North Lenola Road / Moorestown, NJ 08057  
Phone: 856-533-3000 / Fax: 856-533-3003 / [www.cvcthermoset.com](http://www.cvcthermoset.com)



An Emerald Performance Materials<sup>®</sup> Company