

# OMICURE<sup>®</sup> U-52 and OMICURE<sup>®</sup> U-52M

Urea Accelerator  
4,4' Methylene Bis-(Phenyl Dimethyl Urea)  
CAS No. 10097-09-3

## DESCRIPTION

OMICURE<sup>®</sup> U-52, an aromatic substituted urea, is intended for use as a latent accelerator for the dicyandiamide cure of epoxy resins. The addition of OMICURE U-52 to epoxy/dicy formulations produces shelf-stable one-part products that cure in shorter times and/or at lower temperatures. Of the CVC Thermoset Specialties substituted ureas, methylene bis (phenyl dimethyl urea) provides the best combination of acceleration, long shelf life and maintenance of cured properties in dicy-cured DGEBA. OMICURE U-52M represents the micronized grade of OMICURE U-52.

Suggested use levels of OMICURE U-52 in DGEBA/dicy are  $\leq 5$  phr. At 5 phr, curing can be accomplished in about one hour at 100 °C and in less than five minutes at temperatures  $\geq 150$  °C. Room temperature shelf lives (doubling of viscosity) are longer than six months. Cure times and shelf lives are dependent on the composition of the formulated product and your particular end application. Some of the factors that can effect shelf life are formulation ingredients and compounding parameters. Ingredients in which OMICURE U-52 is insoluble at processing and storage temperatures will enhance overall storage stability. OMICURE U-52 can be incorporated into your formulation concurrent with the dicy addition.

## APPLICATIONS

As a latent accelerator in the dicyandiamide cure of epoxy resins used in:

- Adhesives
- Powder coatings
- Prepregs
- Encapsulation
- Reinforcements

### TYPICAL PROPERTIES

Appearance	Off-white to white powder
Melting Point, °C	220 – 230
Moisture Content, max %	0.7
Particle size, U-52, min % smaller than 44 microns	80
Particle size, U-52M (micronized), min % smaller than 44 microns	95

### PERFORMANCE DATA

#### Shelf Life and Tg of OMICURE U-52 Accelerated DGEBA/Dicy

Fomulation, pbw	A	B	C	D	E	F
DGEBA*	100	—————>				
OMICURE DDA-10 (dicyandiamide)	8	—————>				
Hydrophobic fumed silica	3	—————>				
OMICURE U-52	0	1	3	5	-	-
Monuron	-	-	-	-	5	-
Diuron	-	-	-	-	-	5

Room Temperature Shelf Life	A	B	C	D	E	F
Time to double viscosity, weeks	> 70	57	56	52	16	24
Tg, °C**	140	133	127	119	115	115

\*EEW:182-192, 25 °C; Viscosity: 11,000-14,000 cps

\*\*Determined on DSC second scan, first scan to 275 °C, 20 °C per minute

### PACKAGING & AVAILABILITY

OMICURE U-52 (unmicronized) and OMICURE U-52M (micronized) come in plastic-lined corrugated cardboard boxes (net weight 40 lb.) Check with your sales representative for specific designations and particle size specifications.



## HEALTH & SAFETY PRECAUTIONS

OMICURE U-52 is a fine powder classified as a nuisance dust. It is not a primary skin or eye irritant but will cause respiratory irritation with prolonged dust inhalation.

The use of engineering controls to keep the material confined or convey dust away from the breathing zone is the preferred method of handling. Alternatively, an approved dust respirator and impervious clothing should be worn if the material becomes airborne.

Allowing the dust to settle on vegetation may cause harm and may prevent germination.

Refer to CVC Thermoset Specialties Material Safety Data Sheet on OMICURE U-52 for additional safety and health information. The MSDS is revised as new data becomes available.

## DISCLAIMER

The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained there from. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance. Because of the variations in methods, conditions, and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user. CVC Thermoset Specialties shall not be liable for and the customer assumes all risk and liability of any use or handling of any material beyond CVC's direct control. THE SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OR MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner. IN NO EVENT SHALL SELLER BE LIABLE FOR ANY INCIDENTAL, CONSEQUENTIAL OR SPECIAL DAMAGES.