

HyPox[®] UA10

Urethane-Modified Bisphenol A Epoxy Resin
CAS No. 25068-38-6

Test Description	Minimum	Maximum	CVC Test Method
Viscosity @ 25 °C, cps	500,000	800,000	4
EEW, g/eq	210	220	5
Gardner Color	0	2	2

Standard Packaging

Drum: 450 lb.

Pail: 45 lb.

CVC Thermoset Specialties
844 North Lenola Road / Moorestown, NJ 08057
Phone: 856-533-3000 / Fax: 856-533-3003 / www.cvcthermoset.com



An Emerald Performance Materials[®] Company