

## Product Specifications

### Hypro™ 1300X8F CTBN

**Carboxyl-Terminated Butadiene-Acrylonitrile Polymer,  
FDA 21CFR 175.300 Compliant**

<u>Property</u>	<u>Unit</u>	<u>Min</u>	<u>Max</u>
Bound acrylonitrile	%	15.5	19.5
Viscosity	cP @ 27°C	110,000	160,000
Carboxyl	ephr	0.046	0.058
Heat loss	%	0	2.0

Net pail weight, lb: 35

Net drum weight, lb: 425

Manufactured in Akron, Ohio, USA.

Shelf life is twelve months from the month of manufacture in unopened drums stored at temperatures  $\leq 50^{\circ}\text{C}$ .