



An Emerald Performance Materials® Company

Product Specifications

Hypro™ 1300X13F CTBN

Carboxyl-Terminated Butadiene-Acrylonitrile Polymer, FDA 21CFR 175.300 Compliant

Property	Unit	Min	Max
Bound acrylonitrile	%	23.5	27.5
Viscosity	cP @ 27°C	360,000	640,000
Carboxyl content	ephr	0.050	0.064
Heat loss	%	0.0	2.0

Net pail weight, lb: 35

Net drum weight, lb: 400

Manufactured in Akron, Ohio, USA.

Shelf life is twelve months from the month of manufacture in unopened drums stored at temperatures $\leq 50^{\circ}\text{C}$.