

An Emerald Performance Materials Company

Hypro[®] Reactive Liquid Polymers 1300X35 ATBN Amine Terminated Butadiene-Acrylonitrile CAS #68683-29-4/140-31-8

DESCRIPTION

Hypro Reactive Liquid Polymers (RLP) are 100% solids liquid rubbers used to improve the toughness, flexibility, adhesion and impact resistance of thermoset resin systems including epoxies, vinyl esters, unsaturated polyesters, acrylics and urethanes. These materials are a family of butadiene homopolymers and butadiene-acrylonitrile copolymers with functionality at the chain ends. Functional groups are carboxyl (COOH), amine (NH or NH₂), methacrylate or epoxy. The acrylonitrile content varies in these polymers from zero to 26% which directly affects the solubility and glass transition temperature (T_g) of the materials.

Hypro 1300X35 ATBN is an amine terminated butadiene-acrylonitrile copolymer used predominately with other amine functional compounds to improve product performance when added to thermoset resin systems. The amine structure of 1300X35 ATBN is based on -aminoethylpiperazine (N-AEP).

BENEFITS/FEATURES

- Enhances the Toughness/Flexibility of Thermoset Resins
- Improves Adhesion to Difficult to Bond to Substrates
- High-Range Acrylonitrile Containing ATBN (26%)
- Increases Impact Resistance
- Increases Low Temperature Mechanical Properties

TYPICAL USES

- Structural Adhesive Paste
- Composites
- Coatings and Linings for Corrosion Resistance
- Construction Joint Sealers and Mastics
- End uses include Aerospace, Automotive, Construction, Composites and Industrial Applications

TYPICAL PROPERTIES

Appearance	Liquid polymer, amber in color (3 - 8 on the Gardner Color Scale)
Actives Level	100%
Brookfield Viscosity, mPa.s or cP @ 27° C	350,000 - 650,000
Amine Equivalent Weight	600 - 800

STORAGE & HANDLING

To ensure optimal product performance, store material in original unopened containers at or below 50°C.

Hypro ATBN Standard Line of Products —Typical Properties						
Hypro Polymers	2000X173 ATB	1300X21 ATBN	1300X16 ATBN	1300X45 ATBN	1300X35 ATBN	1300X42 ATBN
Acrylonitrile Content, %	0	10	18	18	26	18
Amine Equivalent Weight (AEW)*	950	1,200	900	1,850	700	450
Amine Value	59	47	62	30	80	125
Brookfield Visc. mPa.s or cP @ 27°C (81°F)	180,000	160,000	200,000	375,000	500,000	100,000
Specific Gravity, 25°/25°C (77°F)	-	0.938	0.956	-	0.978	0.942
Glass Transition Temp., T _g , °C**	-	-65	-51	-	-38	-59
Free Amine Level, %	4	2	5	<0.1	7	10

*For secondary amine terminated polymers, AEW value may be used as Amine Hydrogen Equivalent Weight, whereas Hypro 1300X42 ATBN, a primary amine terminated material, Weight per Active Hydrogen is AEW/2.

**Measured via DSC (Differential Scanning Calorimeter).



An Emerald Performance Materials Company

Hypro® 1300X35 ATBN

PACKAGING & AVAILABILITY

Hypro 1300X35 ATBN is available in 55 gal. non-returnable steel drums (net weight 425 lbs.) and 5 gal. plastic pails (35 lbs. net). For further information regarding this material or any other CVC Thermoset Specialties product, please contact your local Sales Representative or our Customer Service Department at 800-296-0040.

DISCLAIMER

The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained there from. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance. Because of the variations in methods, conditions, and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user. CVC Thermoset Specialties shall not be liable for and the customer assumes all risk and liability of any use or handling of any material beyond CVC's direct control. **THE SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OR MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.** Nothing contained herein is to be considered permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner. **IN NO EVENT SHALL SELLER BE LIABLE FOR ANY INCIDENTAL, CONSEQUENTIAL OR SPECIAL DAMAGES.**

CVC Thermoset Specialties—844 N. Lenola Road/Moorestown, NJ 08057
An Emerald Performance Materials Company

© Copyright 2006 Emerald Performance Materials LLC. 6/2006

CVC Thermoset Specialties

844 North Lenola Road / Moorestown, NJ 08057 / Phone: 856-533-3000 / Fax: 856-533-3003 / www.cvcthermoset.com