

Product Specifications

Hypro™ 1300X8 CTBN

Carboxyl-Terminated Butadiene-Acrylonitrile Polymer

| <u>Property</u> | <u>Unit</u> | <u>Min</u> | <u>Max</u> |
|---------------------|-------------|------------|------------|
| Bound acrylonitrile | % | 15.5 | 19.5 |
| Viscosity | cP @ 27°C | 110,000 | 160,000 |
| Carboxyl content | ephr | 0.046 | 0.058 |
| Heat loss | % | 0 | 2.0 |

Net pail weight, lb: 35

Net drum weight, lb: 425

Manufactured in Akron, Ohio, USA.

Shelf life is twelve months from the month of manufacture in unopened drums stored at temperatures $\leq 50^{\circ}\text{C}$