

## Product Specifications

### Hypro™ 1300X9 CTBNX

#### Carboxyl-Terminated Butadiene-Acrylonitrile Polymer

Property	Unit	Min	Max
Bound acrylonitrile	%	15.5	19.5
Viscosity	cP @ 27°C	135,000	185,000
Carboxyl content	ephr	0.061	0.073
Heat loss	%	0.0	2.0

Net pail weight, lb: 35

Net drum weight, lb: 425

Manufactured in Akron, Ohio, USA.

Shelf life is twelve months from the month of manufacture in unopened drums stored at temperatures  $\leq 50^{\circ}\text{C}$ .